

CYTOTOXIC EFFECT OF RED SANDAL MEDIATED SILVER NANOPARTICLES MOUTHWASH USING BRINE SHRIMP LETHALITY ASSAY - AN IN VITRO STUDY

Running Title: Comparative cytotoxic effect silver nanoparticles based mouthwash using brine shrimp lethality assay of Red sandal

ABSTRACT:

Background:

Silver Nanoparticles (AgNP) plays a crucial role in nanoscience, nanotechnology and nanomedicine. AgNP has antibacterial, antifungal, antiviral, anti-inflammatory, anti-antigenic, anticancer and cytotoxic properties. Cytotoxic effects of mouthwashes on the gingival tissue have always been a priority. *Pterocarpus santalinus*, with the common name of red sandalwood. The aim of the study is to evaluate the cytotoxic effect of red sandal mediated silver nanoparticles mouthwash using brine shrimp lethality assay.

Materials and Methods:

The mouthwash was prepared using red sandal mediated silver nanoparticles, ethanol, distilled water, sucrose, sodium benzoate, clove oil, sodium dodecyl phosphate with 0.1% in concentration. The methodology includes green synthesis of Red sanders mediated Silver Nanoparticles synthesis followed by tests for Cytotoxic effect using mouthwash.

Results:

Red sanders mediated silver nanoparticles have high potent cytotoxic potential, it has been proved with the help of brine shrimps. LD50 concentration was obtained to be 80 μ L, with half the population of nauplii in the respective well surviving post incubation.

Conclusion: From the observed result, it has been concluded that *Pterocarpus santalinus*/red sandal mediated silver nanoparticles mouthwash has a considerably moderate cytotoxic effect. It is a rich source of various potential phytochemicals and is a simple, rapid, stable and cost effective method for nano based medical applications.

Keywords: Green synthesis, Cytotoxic effect, Mouthwash, *Pterocarpus santalinus*, Silver nanoparticles

INTRODUCTION:

Various medicinal plants have been used for hundreds of years and are found to be effective in the treatment of many diseases(1). Natural products of plants possess several biological activities including cytotoxic effects. The cytotoxic level of medicinal plants must even be evaluated against host cells. The safety of plants as potential therapeutically agents must be ascertained and the therefore side effects should be acceptable to the host(2). Bioactive compounds with no or less toxic effect to the host are good for formulation of medicine. Many researches are done to understand the cytotoxic effect constituents of medicinal plants for the treatment of the disease(3).

Nanosized inorganic particles, of either simple or composite nature, display physical and chemical properties and represent an increasingly important material development of novel nanodevices which may be utilised in numerous physical, biological, biomedical, and pharmaceutical applications(4). Silver Nanoparticles (AgNP) plays a crucial role in nanoscience, nanotechnology and nanomedicine. AgNP has antibacterial, antifungal, antiviral, anti-inflammatory, anti-antigenic, anticancer and cytotoxic properties(5). AgNP has engrossing properties and its low cost and simply available in natural sources. AgNP has an impractical potential in comparison to gold nanoparticles(6). AgNPs are increasingly utilized in various fields, including medical, food, health care, cosmetics, and industrial purposes, due to their unique physical and chemical properties(7). Silver nanoparticles may be a popular additive in many health products as listed above due to its unique ability to fight infectious diseases, slow the growth of bacteria, mold and germs(8). Biologically prepared AgNPs show high yield, solubility, and high stability(9). Several synthetic methods for AgNPs, biological methods seem to be simple, rapid, non-toxic, dependable, and green approaches which will produce well-defined size and morphology under optimized conditions for translational research(10).

Cytotoxic effects of mouthwashes on the gingival tissue have always been a priority. Chlorhexidine gluconate mouthwash had no cytotoxic effects on human gingival fibroblasts. Mouthwashes are composed of strontium chloride, potassium nitrate, sodium citrate and sodium fluoride as desensitizing agents(11). *Pterocarpus santalinus*, with the common name of red sandalwood. The wood is traditionally considered not aromatic. A wide array of biological activities and potential health benefits of *P. santalinus* have been reported including antioxidative, antidiabetic, antimicrobial, anticancer, anti-inflammatory cytotoxic properties as well as protective effects on the liver, gastric mucosa and nervous systems(12). All these protective effects were attributed to bioactive compounds present in *P. santalinus*. The effect of this herb against most of the oral pathogens is essentially unexplored(13). Our team has extensive knowledge and research experience that has translated into high quality publications (14–26),(27–31),(32),(33). The aim of the study is to evaluate the cytotoxic effect of red sandal mediated silver nanoparticles mouthwash using brine shrimp lethality assay.

MATERIALS AND METHOD:

Preparation of Silver Nanoparticles:

The dried powdered plant material 0.5gm of red sandal was diluted with 100ml of distilled water, and heated for 9 mins at 60-80°C under vacuum. Then it was filtered using Whatman's filter paper and plant extract was prepared. 80ml of distilled water was taken in a conical flask and 20ml of plant extract was added to it. 1mM of Silver particles were added and then kept in a shaker. Preliminary reading was taken every 2 hours for about 72hrs. After 72hrs fill the AgNP plant extract into the 6 centrifuge tube, 12ml each and centrifuged for about 10 mins.

Preparation of mouthwash:

The mouthwash was prepared using red sandal mediated silver nanoparticles, ethanol, distilled water, sucrose, sodium benzoate, clove oil, sodium dodecyl phosphate with 0.1% in concentration. Silver nanoparticles are the main constituent, ethanol acts as a solvent to solubilise the ingredients. Sodium benzoate acts as a preservative and clove oil acts as a flavouring agent.

Cytotoxic effect:

Brine shrimp eggs were obtained from a new aqua laboratory. The seawater was put in a small plastic container(hatching chamber) with a partition for dark (covered) and light areas.

Shrimp eggs were added into the dark side of the chamber while the lamp above the other side (light) will attract the hatched shrimp. After 2 days, when the shrimp were ready, 5 different nanoparticles solution was added to each test tube, 10 shrimps were introduced in each tube. After 24 hrs, the number of surviving shrimps were counted and recorded. LC50 of less than 100 ppm was considered as potent.

RESULTS

The test for cytotoxic properties was assessed using brine shrimps. Descriptive statistics were used in this study. Ten nauplii were placed in each of six wells with one standard and the remaining with nanoparticle concentrations 5 μ L, 10 μ L, 20 μ L, 40 μ L and 80 μ L. LD50 concentration was obtained to be 80 μ L, with half the population of nauplii in the respective well surviving post incubation. 10 numbers of nauplii are alive on day1 in different concentrations. On day 2, 9 nauplii are alive on 5 μ L concentration, 8 nauplii are alive on 10 μ L concentration, 9 nauplii are alive on 20 μ L concentration, 8 nauplii are alive on 40 μ L concentration and 7 nauplii are alive on 80 μ L concentration. All nauplii are alive in control value(Table 1, Figure 1)

Table 1 depicts the cytotoxic activity of red sandal silver nanoparticles mouthwash

Concentration(μ L)	Day 1	Day 2
5 μ L	10	9
10 μ L	10	9
20 μ L	10	9
40 μ L	10	8
80 μ L	10	8
Control	10	10




Figure 1: Graph showing cytotoxic effect of silver nanoparticles based mouthwash of red sandal. Blue represents day 1 and orange represents day 2. X axis denotes number of nauplii alive and Y axis denotes concentration. All nauplii are alive on day 1. On day 2, 9 nauplii are alive in 5µL, 8 nauplii are alive in 10µL, 9 nauplii are alive in 20µL, 8 nauplii are alive in 40µL and 7 nauplii are alive in 80µL. In comparison between day 1 and day 2, as concentration increases, the number nauplii decreases.

DISCUSSION:

Medicinal plants have unlimited capacity to synthesize bioactive compounds that are effective and have fewer side effects compared to synthetic drugs. Bioactive compounds from plants have shown over the years to have various biological activities(34). Scientists have developed a greater interest in using these compounds in formulation of new and novel drugs, because of their biological activities and reliability(35). *P.santalinus* could be used to treat various medical complications such as hemorrhage, dysentery, eye diseases, and mental aberrations, and to act as an aphrodisiac and diaphoretic.

P.santalinus is highly valued for its heavy, dark claret-red sanders, which yields 16% of the red coloring matter santalin, used as a coloring agent in pharmaceutical preparations and

foodstuff (36). The presence of various types of plant secondary metabolites such as anthocyanins, flavonoids, glycerides, isoflavone glucoside, phenols, pterocarpol, pterocarptriol, pterocarpodiolones with β -eudeslrol, saponins, steroids tannins and triterpenoids in the *P. santalinus* L. has been reported ((37).

Cytotoxicity of dental materials and oral hygiene products has always been a concern for dental clinicians. These products should be biocompatible; otherwise, they would cause inflammatory reactions. Nanotechnology favorably changed the properties of many dental materials. Mouthwashes are composed of strontium chloride, potassium nitrate, sodium citrate and sodium fluoride as desensitizing agents. Clinical and human intervention studies are very limited; therefore the biological and physiological effects of the isolated compounds of the heartwood are also worth investigation. The key advances in the tissue culture-based biotechnology of economically important red sandals (38). The development of treatment methods has evoked great expectations in the future. This plant has been exploited to treat a wide variety of ailments, with reported antimicrobial and antioxidant properties, as well as cytotoxic effects against some human cancer cell lines. Invitro cytotoxicity effects of leaf, stem and bark of *Pterocarpus santalinus* Linn.F. was evaluated in a study where they found that *P.santalinus* showed a cytotoxic effect against cancer cell lines(39). The limitation of this study is that we did not do clinical trials in patients.

CONCLUSION:

From the observed result, it has been concluded that *Pterocarpus santalinus*/red sandal mediated silver nanoparticles mouthwash has a considerably moderate cytotoxic effect(40) (41) (42) (43) (44) (45) (46) (47) (48) (49) (50) ((50,51) (52) (53). It is a rich source of various potential phytochemicals and is a simple, rapid, stable and cost effective method for nano based medical applications.

COMPETING INTERESTS DISCLAIMER:

Authors have declared that no competing interests exist. The products used for this research are commonly and predominantly use products in our area of research and country. There is absolutely no conflict of interest between the authors and producers of the products because we do not intend to use these products as an avenue for any litigation but for the advancement of knowledge. Also, the research was not funded by the producing company rather it was funded by personal efforts of the authors.

REFERENCES:

1. Das K, Gowthami V, Dang R. Comparative proximate analysis, phytochemical screening and antioxidant study of leaf and root extracts of *Decalepis hamiltonii* Wight & Arn [Internet]. Vol. 6, *Annals of Phytomedicine: An International Journal*. 2017. Available from: <http://dx.doi.org/10.21276/ap.2017.6.2.12>
2. Gurunathan S, Park JH, Han JW, Kim J-H. Comparative assessment of the apoptotic potential of silver nanoparticles synthesized by *Bacillus tequilensis* and *Calocybe indica* in MDA-MB-231 human breast cancer cells: targeting p53 for anticancer therapy. *Int J Nanomedicine* [Internet]. 2015 Jun 29;10:4203–22. Available from: <http://dx.doi.org/10.2147/IJN.S83953>
3. Breuer U. *Plastics from Bacteria - Natural Functions and Applications*. By Guo-Qiang Chen (Editor), Alexander Steinbüchel (Series Editor) [Internet]. Vol. 5, *Biotechnology Journal*. 2010. p. 1351–1351. Available from: <http://dx.doi.org/10.1002/biot.201090064>
4. Paul RP, Roy A, Maajida AM, Shanmugam R. Antibacterial Activity of White Pepper Oleoresin Mediated Silver Nanoparticles against Oral Pathogens [Internet]. Vol. 9, *Journal of Evolution of Medical and Dental Sciences*. 2020. p. 2352–5. Available from: <http://dx.doi.org/10.14260/jemds/2020/510>
5. Lal HM. *Polymer Nanocomposites Based on Silver Nanoparticles: Synthesis, Characterization and Applications* [Internet]. Springer Nature; Available from: https://books.google.com/books/about/Polymer_Nanocomposites_Based_on_Silver_N.h tml?hl=&id=G00dEAAAQBAJ
6. Chernousova S, Epple M. Silver as Antibacterial Agent: Ion, Nanoparticle, and Metal [Internet]. Vol. 52, *Angewandte Chemie International Edition*. 2013. p. 1636–53. Available from: <http://dx.doi.org/10.1002/anie.201205923>
7. Wang H, Li L-L. *In Vivo Self-Assembly Nanotechnology for Biomedical Applications* [Internet]. Springer; 2018. 201 p. Available from: <https://play.google.com/store/books/details?id=14pWDwAAQBAJ>
8. Lofrano G, Libralato G, Brown J. *Nanotechnologies for Environmental Remediation: Applications and Implications* [Internet]. Springer; 2017. 325 p. Available from: <https://play.google.com/store/books/details?id=eMZCDgAAQBAJ>
9. Li L-S, Hu J, Yang W, Paul Alivisatos A. Band Gap Variation of Size- and Shape-Controlled Colloidal CdSe Quantum Rods [Internet]. Vol. 1, *Nano Letters*. 2001. p. 349–51. Available from: <http://dx.doi.org/10.1021/nl015559r>
10. Karthik L, Vishnu Kirthi A, Ranjan S, Mohana Srinivasan V. *Biological Synthesis of Nanoparticles and Their Applications* [Internet]. CRC Press; 2019. 284 p. Available from: <https://play.google.com/store/books/details?id=QtzBDwAAQBAJ>

11. Coelho AS, Laranjo M, Gonçalves AC, Paula A, Paulo S, Abrantes AM, et al. Cytotoxic effects of a chlorhexidine mouthwash and of an enzymatic mouthwash on human gingival fibroblasts. *Odontology* [Internet]. 2020 Apr;108(2):260–70. Available from: <http://dx.doi.org/10.1007/s10266-019-00465-z>
12. Manjunatha BK. Hepatoprotective activity of *Pterocarpus santalinus* L.f., an endangered medicinal plant [Internet]. Vol. 38, *Indian Journal of Pharmacology*. 2006. p. 25. Available from: <http://dx.doi.org/10.4103/0253-7613.19848>
13. Bindhu MR, Umadevi M. Antibacterial activities of green synthesized gold nanoparticles [Internet]. Vol. 120, *Materials Letters*. 2014. p. 122–5. Available from: <http://dx.doi.org/10.1016/j.matlet.2014.01.108>
14. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. *J Periodontol* [Internet]. 2018 Oct;89(10):1241–8. Available from: <http://dx.doi.org/10.1002/JPER.17-0445>
15. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. *Hypertens Res* [Internet]. 2020 Jul;43(7):729–30. Available from: <http://dx.doi.org/10.1038/s41440-020-0461-x>
16. S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. *Int J Biol Macromol* [Internet]. 2018 Dec;120(Pt A):876–85. Available from: <http://dx.doi.org/10.1016/j.ijbiomac.2018.08.149>
17. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. *Cochrane Database Syst Rev* [Internet]. 2018 Nov 26;11:CD011423. Available from: <http://dx.doi.org/10.1002/14651858.CD011423.pub2>
18. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. *Hypertens Res* [Internet]. 2020 Aug;43(8):851–3. Available from: <http://dx.doi.org/10.1038/s41440-020-0423-3>
19. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. *Cell Mol Immunol* [Internet]. 2019 Dec;16(12):935–6. Available from: <http://dx.doi.org/10.1038/s41423-019-0310-5>
20. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm. *Comput Commun* [Internet]. 2019 Dec 15;148:176–84. Available from: <https://www.sciencedirect.com/science/article/pii/S0140366419307017>
21. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). *J Med Syst* [Internet]. 2018 Aug 29;42(10):183. Available from: <http://dx.doi.org/10.1007/s10916-018-1037-z>

22. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ* [Internet]. 2019 Apr;83(4):445–50. Available from: <http://dx.doi.org/10.21815/JDE.019.054>
23. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating. *Molecules* [Internet]. 2018 Jun 12;23(6). Available from: <http://dx.doi.org/10.3390/molecules23061429>
24. Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. *Biomolecules* [Internet]. 2018 Aug 1;8(3). Available from: <http://dx.doi.org/10.3390/biom8030068>
25. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from Cuttlefish Bone: Isolation, Characterizations, and Applications. *Biotechnol Bioprocess Eng* [Internet]. 2018 Aug 1;23(4):383–93. Available from: <https://doi.org/10.1007/s12257-018-0169-9>
26. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network. *Measurement* [Internet]. 2019 Mar 1;135:672–7. Available from: <https://www.sciencedirect.com/science/article/pii/S0263224118311333>
27. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod* [Internet]. 2021 Aug;47(8):1198–214. Available from: <http://dx.doi.org/10.1016/j.joen.2021.04.022>
28. R H, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, Krishnan RP. Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris-A review. *Oral Dis* [Internet]. 2021 Jun 21; Available from: <http://dx.doi.org/10.1111/odi.13937>
29. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis* [Internet]. 2021 Feb 11; Available from: <http://dx.doi.org/10.1111/odi.13798>
30. Sarode SC, Gondivkar S, Sarode GS, Gadbail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol* [Internet]. 2021 Jun 16;105390. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105390>
31. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol* [Internet]. 2021 Jun 14;105375. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105375>
32. Vellappally S, Abdullah Al-Kheraif A, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network. *J*

Ambient Intell Humaniz Comput [Internet]. 2018 Dec 14; Available from: <https://doi.org/10.1007/s12652-018-1166-8>

33. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. Risk Manag Healthc Policy [Internet]. 2021 Jul 7;14:2851–61. Available from: <http://dx.doi.org/10.2147/RMHP.S306880>
34. Cruz D, Falé PL, Mourato A, Vaz PD, Luisa Serralheiro M, Lino ARL. Preparation and physicochemical characterization of Ag nanoparticles biosynthesized by *Lippia citriodora* (Lemon Verbena) [Internet]. Vol. 81, Colloids and Surfaces B: Biointerfaces. 2010. p. 67–73. Available from: <http://dx.doi.org/10.1016/j.colsurfb.2010.06.025>
35. Dash SS, Bag BG. Synthesis of gold nanoparticles using renewable *Punica granatum* juice and study of its catalytic activity [Internet]. Vol. 4, Applied Nanoscience. 2014. p. 55–9. Available from: <http://dx.doi.org/10.1007/s13204-012-0179-4>
36. Krishnaveni KS, Srinivasa Rao JV. A New Acylated Isoflavone Glucoside from *Pterocarpus santalinus* [Internet]. Vol. 48, Chemical and Pharmaceutical Bulletin. 2000. p. 1373–4. Available from: <http://dx.doi.org/10.1248/cpb.48.1373>
37. Balaraju K, Agastian P, Ignacimuthu S, Park K. A rapid in vitro propagation of red sanders (*Pterocarpus santalinus* L.) using shoot tip explants [Internet]. Vol. 33, Acta Physiologiae Plantarum. 2011. p. 2501–10. Available from: <http://dx.doi.org/10.1007/s11738-011-0795-8>
38. Arunkumar AN, Joshi G. *Pterocarpus santalinus* (Red Sanders) an Endemic, Endangered Tree of India: Current Status, Improvement and the Future [Internet]. Vol. 4, Journal of Tropical Forestry and Environment. 2014. Available from: <http://dx.doi.org/10.31357/jtfe.v4i2.2063>
39. Donga S, Moteriya P, Chanda S. EVALUATION OF ANTIMICROBIAL AND SYNERGISTIC ANTIMICROBIAL PROPERTIES OF PTEROCARPUS SANTALINUS [Internet]. Vol. 10, Asian Journal of Pharmaceutical and Clinical Research. 2017. p. 204. Available from: <http://dx.doi.org/10.22159/ajpcr.2017.v10i11.20939>
40. Danda AK. Comparison of a single noncompression miniplate versus 2 noncompression miniplates in the treatment of mandibular angle fractures: a prospective, randomized clinical trial. J Oral Maxillofac Surg [Internet]. 2010 Jul;68(7):1565–7. Available from: <http://dx.doi.org/10.1016/j.joms.2010.01.011>
41. Robert R, Justin Raj C, Krishnan S, Jerome Das S. Growth, theoretical and optical studies on potassium dihydrogen phosphate (KDP) single crystals by modified Sankaranarayanan–Ramasamy (mSR) method [Internet]. Vol. 405, Physica B: Condensed Matter. 2010. p. 20–4. Available from: <http://dx.doi.org/10.1016/j.physb.2009.08.015>
42. Krishnan V, Lakshmi T. Bioglass: A novel biocompatible innovation. J Adv Pharm Technol Res [Internet]. 2013 Apr;4(2):78–83. Available from: <http://dx.doi.org/10.4103/2231-4040.111523>

43. Soh CL, Narayanan V. Quality of life assessment in patients with dentofacial deformity undergoing orthognathic surgery—A systematic review [Internet]. Vol. 42, International Journal of Oral and Maxillofacial Surgery. 2013. p. 974–80. Available from: <http://dx.doi.org/10.1016/j.ijom.2013.03.023>
44. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Schiff base complexes of rare earth metal ions: Synthesis, characterization and catalytic activity for the oxidation of aniline and substituted anilines [Internet]. Vol. 753, Journal of Organometallic Chemistry. 2014. p. 72–80. Available from: <http://dx.doi.org/10.1016/j.jorganchem.2013.12.014>
45. Dhinesh B, Isaac Joshua Ramesh Lalvani J, Parthasarathy M, Annamalai K. An assessment on performance, emission and combustion characteristics of single cylinder diesel engine powered by Cymbopogon flexuosus biofuel [Internet]. Vol. 117, Energy Conversion and Management. 2016. p. 466–74. Available from: <http://dx.doi.org/10.1016/j.enconman.2016.03.049>
46. PradeepKumar AR, Shemesh H, Jothilatha S, Vijayabharathi R, Jayalakshmi S, Kishen A. Diagnosis of Vertical Root Fractures in Restored Endodontically Treated Teeth: A Time-dependent Retrospective Cohort Study. J Endod [Internet]. 2016 Aug;42(8):1175–80. Available from: <http://dx.doi.org/10.1016/j.joen.2016.04.012>
47. Vijayakumar GNS, Nixon Samuel Vijayakumar G, Devashankar S, Rathnakumari M, Sureshkumar P. Synthesis of electrospun ZnO/CuO nanocomposite fibers and their dielectric and non-linear optic studies [Internet]. Vol. 507, Journal of Alloys and Compounds. 2010. p. 225–9. Available from: <http://dx.doi.org/10.1016/j.jallcom.2010.07.161>
48. Kavitha M, Subramanian R, Narayanan R, Udhayabanu V. Solution combustion synthesis and characterization of strontium substituted hydroxyapatite nanocrystals [Internet]. Vol. 253, Powder Technology. 2014. p. 129–37. Available from: <http://dx.doi.org/10.1016/j.powtec.2013.10.045>
49. Sahu D, Kannan GM, Vijayaraghavan R. Size-Dependent Effect of Zinc Oxide on Toxicity and Inflammatory Potential of Human Monocytes [Internet]. Vol. 77, Journal of Toxicology and Environmental Health, Part A. 2014. p. 177–91. Available from: <http://dx.doi.org/10.1080/15287394.2013.853224>
50. Neelakantan P, Cheng CQ, Mohanraj R, Sriraman P, Subbarao C, Sharma S. Antibiofilm activity of three irrigation protocols activated by ultrasonic, diode laser or Er:YAG laser in vitro [Internet]. Vol. 48, International Endodontic Journal. 2015. p. 602–10. Available from: <http://dx.doi.org/10.1111/iej.12354>
51. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Synthesis, spectroscopic characterization and antibacterial studies of lanthanide(III) Schiff base complexes containing N, O donor atoms [Internet]. Vols. 1056-1057, Journal of Molecular Structure. 2014. p. 307–13. Available from: <http://dx.doi.org/10.1016/j.molstruc.2013.10.014>
52. Gopalakannan S, Senthilvelan T, Ranganathan S. Modeling and Optimization of EDM Process Parameters on Machining of Al 7075-B4C MMC Using RSM [Internet]. Vol.

38, Procedia Engineering. 2012. p. 685–90. Available from:
<http://dx.doi.org/10.1016/j.proeng.2012.06.086>

53. Parthasarathy M, Isaac JoshuaRamesh Lalvani J, Dhinesh B, Annamalai K. Effect of hydrogen on ethanol-biodiesel blend on performance and emission characteristics of a direct injection diesel engine. Ecotoxicol Environ Saf [Internet]. 2016 Dec;134(Pt 2):433–9. Available from: <http://dx.doi.org/10.1016/j.ecoenv.2015.11.005>

UNDER PEER REVIEW