

EVALUATION OF THE ANTIOXIDANT ACTIVITY OF BANANA STEM MEDIATED COPPER NANOPARTICLES : AN IN VITRO STUDY

ABSTRACT

Background: *Musa sapientum*, commonly known as banana, is an herbaceous plant of the Musaceae family. Copper-based nanoparticles (Cu-NPs) enhance the scavenging capacity of various antioxidants and improve the treatment of ROS-related diseases. The aim of this study is to evaluate the antioxidant activity of banana stem mediated copper nanoparticles.

Materials and Methods: Banana stems weighing 200 grams were cut into small pieces. These fragments were powdered and mixed with 200 cc of sterile distilled water in a blender. $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$ (0.5 mmol, 5 mL) was applied to ethanol, and the reaction mixture was allowed to react with 1 M NaOH while stirring. Cu-Nps and the prepared banana stem extract were mixed together. The DPPH assay was used to investigate the antioxidant activity of banana stem mediated Cu-Nps. The percent inhibition values were determined using the formula after the absorbance values were measured with a UV spectrophotometer.

Results: At the highest concentration used in the study, the antioxidant activity of banana stem mediated Cu-Nps was 88.10 percent and that of vitamin C was 92.15 percent. This demonstrated that Cu- Nps mediated by banana stems have a concentration-dependent antioxidant effect.

Conclusion: The antioxidant activity of banana stem mediated Cu- Nps tested here was higher than the standard antioxidant drug vitamin c in lower concentration. In higher concentration, vitamin c standard showed higher antioxidant activity.

Keywords: antioxidant; banana stem; copper nanoparticles; DPPH assay; green synthesis

INTRODUCTION

Wounds are physical factors that cause tissue damage and disrupt the normal tissue integrity structure. The wound can be divided into two types based on the extent of tissue damage: open wounds and closed wounds. However, the healing process for such wounds is essentially the same, but the pace of healing is determined by the infection, surgical operation, and medication used(1). The healing process for a tooth extraction includes many steps, including hemostasis (blood clot formation), inflammation (leukocyte infiltration), proliferation (connective tissue formation), granulation and epithelialization stages, and remodelling level(2). As a result, local therapy may be used to reduce systemic effects and avoid unnecessary bleeding, ensuring that the healing process is not hampered(3). Inflammation is often a complicated reaction to the injury's causative agents, such as microbial and cell harm(4). Since it can kill the causative agents of inflammatory lesions and set off a sequence of events aimed at healing or repairing damaged tissue, the inflammatory response is closely linked to the healing process.

Reactive oxygen species (ROS) are increased by phagocytic cells during tooth extraction. (PMN) (5). Oxidants can be involved in different pathological processes in the body as a result of reactive oxygen compounds(6). Oxidants and free radicals are often confused in the medical field because they have identical properties. Antioxidants are medicines that can reduce the activity of free radicals. At their "physiological concentrations," free radicals or ROS may regulate cell growth, differentiation, cell adhesion, cell senescence, and apoptosis. However, if a high concentration of ROS or more than antioxidants is obtained in the body, ROS can be destructive. As a result, ROS can oxidise fat and protein while also damaging DNA through DNA fragmentation(7). Furthermore, chronic inflammation and tissue damage are thought to be caused by repeated exposure to ROS. Endothelial dysfunction and tissue damage can be caused by increased ROS in inflamed tissue. Antioxidant levels in the body decrease as people age, slowing

the healing process. Antioxidants such as catalase, superoxide dismutase, and glutathione peroxidase can neutralise ROS(8).

Musa sapientum, commonly known as banana, is an herbaceous plant of the Musaceae family. Polyphenols, flavonoids, saponins, anthraquinone, and tannin found in banana stem sap can trap free radicals and prevent cell damage(9). Furthermore, due to the activation of clotting factors and the response of endothelial glycoprotein-Ib, fresh banana stem extract can reduce bleeding and clotting time (GPIB). Glycoprotein aids platelet adhesion to endothelium, allowing activated platelets to release granule contents during the healing process. Copper-based nanoparticles (Cu-NPs) enhance the scavenging capacity of various antioxidants and improve the treatment of ROS-related diseases. Copper (Cu) is one of the best elements for human use, as it is involved in tyrosinase and the Cu-ZnSOD enzyme. Connective tissue biosynthesis, cellular respiration, neurotransmitter processing, iron homeostasis, peptide biogenesis, pigment formation, and antioxidant protection are all examples of bioactivities that trigger Cu enzyme activity(10). Cu-NPs, in particular, have excellent catalytic activity for scavenging H₂O₂ and O₂ but not OH, and can also stimulate electron transfer reactions to inactivate H₂O₂ or OH. The catalytic activity of Cu compounds in organic reactions prompted us to concentrate our research on the use of Cu-Nps. As a consequence, we believe that Cu-Nps potential serves as both a catalytic and an antioxidant activity at the same time. Furthermore, the stability of Cu-NPs can be greatly improved, which improves the overall ROS scavenging ability (10,11). This research aims to evaluate the antioxidant activity of banana stem mediated copper nanoparticles.

MATERIALS AND METHODS

Preparation of Extract

Banana stems were cut into small pieces weighing 200 grams in the middle. These fragments were powdered and mixed with 200 cc of sterile distilled water in a blender. Five minutes were spent blending those parts until they were fully smooth. Whatman filter paper no. 1 was used to filter it. (Figure 1).

Preparation of Cu-Nps

CuCl₂H₂O (0.5 mmol, 5 mL) was applied to ethanol, and the reaction mixture was allowed to react with 1 M NaOH while stirring. The blue precipitate was formed after adding 15 mL of water to the reaction mixture. The precipitate was filtered and distilled using appropriate methods. (Figure 1) The prepared banana stem extract and Cu-Nps were mixed together.

Antioxidant assay – DPPH assay

The DPPH (1,1-diphenyl-2-picryl-hydrazil) free radical scavenging activity of prepared banana stem extract was determined according to the method of Rajeshkumar (Figure 2). Different concentrations (2-10 µg/ml) of banana stem extract were mixed with 1 mL of 0.1 mM DPPH in methanol solution and 450 µL of 50 mM TrisHCl buffer (pH 7.4) and incubated for 30 minutes. After incubation, the reduction in the number of DPPH free radicals was measured based on the absorbance at 517 nm. BHT was used as control. The percentage inhibition was calculated from the following equation :

$$\% \text{ INHIBITION} = \frac{\text{Absorbance of control} - \text{Absorbance of sample}}{\text{Absorbance of Control}} \times 100$$

where the absorbance of control is 1.




Figure 1: Preparation of Banana stem extract and Cu- Nps



Figure 2: Dpph assay

RESULTS

The results of the antioxidant activity were tabulated and studied as shown in table 1 and figure 3. The results suggest that the % inhibition values are higher than the standard vitamin C at every concentration and so was the antioxidant activity as shown in Figure 3. Descriptive statistics was followed. The antioxidant activity of the banana stem mediated Cu- Nps at 10 μ L was 86.10% whereas that of the vitamin c was 25.03 %. The banana stem mediated Cu- Nps showed a higher antioxidant activity by 61.07%. The antioxidant activity of banana stem mediated Cu- Nps at 20 μ L was 86.10% whereas that of the vitamin c was 51.13 %. The antioxidant activity of banana stem mediated Cu- Nps at 30 μ L was 87.60% whereas that of the vitamin c was 65.54 %. The antioxidant activity of banana stem mediated Cu- Nps at 40 μ L was 87.90% whereas that of the vitamin c was 78.68%.

The banana stem mediated Cu- Nps showed a higher antioxidant activity compared to control, Unlike other concentrations of banana stem mediated Cu- Nps, at the highest concentration (50 μ L) vitamin C showed a higher antioxidant activity when compared to the banana stem mediated Cu- Nps. The antioxidant activity of banana stem mediated Cu- Nps was 88.10% and that of vitamin C was 92.15%. Hence, it could be concluded that the antioxidant activity of banana stem mediated Cu- Nps tested here was higher than the standard antioxidant drug vitamin c in lower concentration. In higher concentration, vitamin c showed higher antioxidant activity (Table 1, Figure 3).

Table 1: Table compares the percentage inhibition produced by banana stem mediated Cu-Nps with standard Vitamin C

CONCENTRATION (μL)	% INHIBITION OF VITAMIN C	% INHIBITION OF TEST
10	25.03	86.10
20	51.13	86.10
30	65.54	87.60
40	78.68	87.90
50	92.15	88.10




Figure 3: Graph comparing the antioxidant activity of banana stem mediated Cu- Nps with standard vitamin C, while X -axis shows the different concentrations of banana stem mediated Cu- Nps and Vitamin C while Y axis shows % inhibition values obtained. Blue color indicates % inhibition of vitamin C in various concentrations while orange color indicates % inhibition of test

sample in various concentrations. The antioxidant activity of banana stem mediated Cu- Nps tested here was higher than the standard antioxidant drug vitamin c in lower concentration. In higher concentration, vitamin c (standard) showed higher antioxidant activity. A concentration dependent antioxidant activity was observed.

DISCUSSION

Our team has extensive knowledge and research experience that has translated into high quality publications (12–24),(25–29),(30),(31). In the present study, activity of banana stem mediating Cu-Nps to scavenge the harmful free radicals or unstable molecules produced during normal metabolism, that possess the ability to damage the cells of our body, was studied by analyzing the ability to scavenge DPPH. Free radical damage contributes to the etiology of many chronic health problems such as cardiovascular and inflammatory disease, cataract, and cancer. Hence, calculating antioxidant activity enables us to nullify these ill effects caused by antioxidants. As part of the wound healing process, wounds caused by medical attention can trigger an inflammatory response. Vascular permeability can be increased by the release of inflammatory mediators such as bradykinin, histamine, and free radicals from leukocytes. A large number of free radicals can cause cell damage, reduce the cell's ability to adapt to the environment, and inhibit the cell's ability to heal quickly(32).

Ascorbic acid, also known as vitamin C, is a six-lactone carbon atom produced by the liver from glucose. The atoms of vitamin C donate H + or H that is oxidised by ROS, resulting in neutral tricarbonyl ascorbate free radicals. In addition, as compared to other compounds, vitamin C is a compound with a high antioxidant activity. Vitamin C has antioxidant activity of 92.15% in this study, indicating that it can function as an antioxidant according to the norm IC50 (32,33). According to the findings, the antioxidant activity of the banana stem mediated Cu- Nps was 87.70% at 30µL, 87.90% at 40µL, and 88.10 percent at 50µL, indicating that those scores are in line with the appropriate IC50 norm. As a result, the antioxidant activity of the banana stem extract concentrations can be inferred (34). Furthermore, flavonoids found in green banana stem sap can induce antioxidant activity. Since they contain hydroxyl groups, these compounds serve

as free radical trappers. Flavonoids can thus serve as hydrogen donors against free radicals as reducing agents (35),(36).

Because of the crude extract, a solution of vitamin C as a positive control (+) has lower antioxidant activity than the banana stem extract used (37). The crude extract does, however, contain several compounds that can be collected, such as flavonoids, saponins, and polyphenols, as well as antioxidant tannins. Vitamin C, on the other hand, is a single molecule. Some of the compounds in the crude extract of banana stem sap have a different ROS damping function, reducing a wide variety of ROS ((38). The copper nanoparticles utilized in this study were not tested in patients which could be a possible limitation of this study. In conclusion, antioxidant activities found in all of the banana stem concentrations indicate that the banana stem has the potential to be developed as a biomaterial for wound healing in the future (39-52).

CONCLUSION

The antioxidant activity of banana stem mediated Cu- Nps tested here was higher than the standard antioxidant drug vitamin c in lower concentration. In higher concentration, vitamin c standard showed higher antioxidant activity. A concentration dependent antioxidant activity was observed.

REFERENCES

1. Altoé LS, Alves RS, Miranda LL, Sarandy MM, Bastos DSS, Gonçalves-Santos E, et al. Doxycycline Hyclate Modulates Antioxidant Defenses, Matrix Metalloproteinases, and COX-2 Activity Accelerating Skin Wound Healing by Secondary Intention in Rats. *Oxid Med Cell Longev* [Internet]. 2021 Apr 17;2021:4681041. Available from: <http://dx.doi.org/10.1155/2021/4681041>
2. Ohadi M, Forootanfar H, Rahimi HR, Jafari E, Shakibaie M, Eslaminejad T, et al. Antioxidant Potential and Wound Healing Activity of Biosurfactant Produced by *Acinetobacter junii* B6 [Internet]. Vol. 18, *Current Pharmaceutical Biotechnology*. 2018. p. 900–8. Available from: <http://dx.doi.org/10.2174/1389201018666171122121350>
3. Vuotto C. Chitosan derivatives with antioxidant and antimicrobial activity for wound

dressing applications [Internet]. Available from:
<http://dx.doi.org/10.26226/morressier.56d5ba30d462b80296c955a3>

4. Tatke P. Antioxidant, Antimicrobial And Wound Healing Activity Of *Salvadora persica* Twig Extracts [Internet]. Vol. 7, *Journal of Complementary Medicine & Alternative Healthcare*. 2018. Available from: <http://dx.doi.org/10.19080/jcmah.2018.07.555720>
5. Jebakumar KTS, Sujin Jebakumar KT. Excision Wound Healing and Antioxidant Activity of Different Root Extract of *Plumbago indica* [Internet]. *Medicinal Plant Research*. 2013. Available from: <http://dx.doi.org/10.5376/mpr.2013.03.0003>
6. Bagyalakshmi B, Nivedhitha P, Balamurugan A. Studies on phytochemical analysis, antioxidant and antibacterial activity of *Ficus racemosa* L. leaf and fruit extracts against wound pathogens [Internet]. Vol. 32, *Vegetos*. 2019. p. 58–63. Available from: <http://dx.doi.org/10.1007/s42535-019-00007-6>
7. A. LM, Lekganyane MA. The phytochemical, antibacterial and antioxidant activity of five medicinal plants against the wound infecting bacteria [Internet]. Vol. 11, *AFRICAN JOURNAL OF BIOTECHNOLOGY*. 2012. Available from: <http://dx.doi.org/10.5897/ajb12.885>
8. Aslantürk ÖS, Çelik TA, Sönmez YM. Investigation of Antioxidant and In Vitro Wound Healing Activity of Fulvic Acid [Internet]. *Journal of the Institute of Science and Technology*. 2019. p. 1316–26. Available from: <http://dx.doi.org/10.21597/jist.509971>
9. Zainol N. Kinetics of Biogas Production from Banana Stem Waste [Internet]. *Biogas*. 2012. Available from: <http://dx.doi.org/10.5772/33196>
10. Rishikesan S, Basha MAM. Synthesis, Characterization and Evaluation of Antimicrobial, Antioxidant & Anticancer Activities of Copper Doped Zinc Oxide Nanoparticles. *Acta Chim Slov* [Internet]. 2020 Mar;67(1):235–45. Available from: <https://www.ncbi.nlm.nih.gov/pubmed/33558933>
11. Naafs MAB. Copper Nanoparticles and Antioxidant Stress: Problem Makers or Solvers? [Internet]. Vol. 3, *Novel Techniques in Nutrition & Food Science*. 2019. Available from: <http://dx.doi.org/10.31031/ntnf.2019.03.000557>
12. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. *J Periodontol* [Internet]. 2018 Oct;89(10):1241–8. Available from: <http://dx.doi.org/10.1002/JPER.17-0445>
13. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. *Hypertens Res* [Internet]. 2020 Jul;43(7):729–30. Available from: <http://dx.doi.org/10.1038/s41440-020-0461-x>
14. S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications.

- Int J Biol Macromol [Internet]. 2018 Dec;120(Pt A):876–85. Available from: <http://dx.doi.org/10.1016/j.ijbiomac.2018.08.149>
15. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. *Cochrane Database Syst Rev* [Internet]. 2018 Nov 26;11:CD011423. Available from: <http://dx.doi.org/10.1002/14651858.CD011423.pub2>
 16. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. *Hypertens Res* [Internet]. 2020 Aug;43(8):851–3. Available from: <http://dx.doi.org/10.1038/s41440-020-0423-3>
 17. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. *Cell Mol Immunol* [Internet]. 2019 Dec;16(12):935–6. Available from: <http://dx.doi.org/10.1038/s41423-019-0310-5>
 18. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm. *Comput Commun* [Internet]. 2019 Dec 15;148:176–84. Available from: <https://www.sciencedirect.com/science/article/pii/S0140366419307017>
 19. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). *J Med Syst* [Internet]. 2018 Aug 29;42(10):183. Available from: <http://dx.doi.org/10.1007/s10916-018-1037-z>
 20. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ* [Internet]. 2019 Apr;83(4):445–50. Available from: <http://dx.doi.org/10.21815/JDE.019.054>
 21. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating. *Molecules* [Internet]. 2018 Jun 12;23(6). Available from: <http://dx.doi.org/10.3390/molecules23061429>
 22. Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. *Biomolecules* [Internet]. 2018 Aug 1;8(3). Available from: <http://dx.doi.org/10.3390/biom8030068>
 23. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from Cuttlefish Bone: Isolation, Characterizations, and Applications. *Biotechnol Bioprocess Eng* [Internet]. 2018 Aug 1;23(4):383–93. Available from: <https://doi.org/10.1007/s12257-018-0169-9>
 24. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for

monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network. Measurement [Internet]. 2019 Mar 1;135:672–7. Available from: <https://www.sciencedirect.com/science/article/pii/S0263224118311333>

25. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. J Endod [Internet]. 2021 Aug;47(8):1198–214. Available from: <http://dx.doi.org/10.1016/j.joen.2021.04.022>
26. R H, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, Krishnan RP. Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris-A review. Oral Dis [Internet]. 2021 Jun 21; Available from: <http://dx.doi.org/10.1111/odi.13937>
27. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. Oral Dis [Internet]. 2021 Feb 11; Available from: <http://dx.doi.org/10.1111/odi.13798>
28. Sarode SC, Gondivkar S, Sarode GS, Gadail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. Oral Oncol [Internet]. 2021 Jun 16;105390. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105390>
29. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. Oral Oncol [Internet]. 2021 Jun 14;105375. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105375>
30. Vellappally S, Abdullah Al-Kheraif A, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network. J Ambient Intell Humaniz Comput [Internet]. 2018 Dec 14; Available from: <https://doi.org/10.1007/s12652-018-1166-8>
31. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. Risk Manag Healthc Policy [Internet]. 2021 Jul 7;14:2851–61. Available from: <http://dx.doi.org/10.2147/RMHP.S306880>
32. Hossain AS, Uddin MM. Callus cell, shoot and stem proliferation data from pineapple crown and banana inflorescence in vitro: Biochemical and antioxidant properties. Data Brief [Internet]. 2017 Feb;10:340–5. Available from: <http://dx.doi.org/10.1016/j.dib.2016.11.097>
33. Antioxidant and Antimicrobial Activity in Flower and Stem of Banana (*Musa acuminata* “Berangan” and *Musa X paradisiaca* “Nangka”) [Internet]. Vol. 2, Proceedings International. 2020. p. 69. Available from: <http://dx.doi.org/10.33263/proceedings21.069069>
34. Budhalakoti N. Evaluation of β -Carotene Content and Antioxidant Activity of Banana Peels and Banana Peel Extracted Insoluble Dietary Fibres [Internet]. Vol. 11, International

Journal of Agriculture, Environment and Biotechnology. 2018. Available from:
<http://dx.doi.org/10.30954/0974-1712.10.2018.10>

35. Evaluation of Antioxidant Activity of Banana Peels (*Musa acuminata*) Extracts Using Different Extraction Methods [Internet]. *Chemical Science Transactions*. 2015. Available from: <http://dx.doi.org/10.7598/cst2015.921>
36. Vijayakumar S, Presannakumar G, Vijayalakshmi NR. Antioxidant activity of banana flavonoids [Internet]. Vol. 79, *Fitoterapia*. 2008. p. 279–82. Available from: <http://dx.doi.org/10.1016/j.fitote.2008.01.007>
37. Sathya M. Assaying the Antioxidant Activity of Banana Peel [Internet]. Vol. 4, *American Journal of Biochemistry and Molecular Biology*. 2014. p. 122–9. Available from: <http://dx.doi.org/10.3923/ajbmb.2014.122.129>
38. Koon SS. Antimicrobial and Antioxidant Activity of Banana by Products [Internet]. 2009. 90 p. Available from: https://books.google.com/books/about/Antimicrobial_and_Antioxidant_Activity_o.html?hl=&id=fqYHtAECAAJ
39. Danda AK. Comparison of a single noncompression miniplate versus 2 noncompression miniplates in the treatment of mandibular angle fractures: a prospective, randomized clinical trial. *J Oral Maxillofac Surg* [Internet]. 2010 Jul;68(7):1565–7. Available from: <http://dx.doi.org/10.1016/j.joms.2010.01.011>
40. Robert R, Justin Raj C, Krishnan S, Jerome Das S. Growth, theoretical and optical studies on potassium dihydrogen phosphate (KDP) single crystals by modified Sankaranarayanan–Ramasamy (mSR) method [Internet]. Vol. 405, *Physica B: Condensed Matter*. 2010. p. 20–4. Available from: <http://dx.doi.org/10.1016/j.physb.2009.08.015>
41. Krishnan V, Lakshmi T. Bioglass: A novel biocompatible innovation. *J Adv Pharm Technol Res* [Internet]. 2013 Apr;4(2):78–83. Available from: <http://dx.doi.org/10.4103/2231-4040.111523>
42. Soh CL, Narayanan V. Quality of life assessment in patients with dentofacial deformity undergoing orthognathic surgery—A systematic review [Internet]. Vol. 42, *International Journal of Oral and Maxillofacial Surgery*. 2013. p. 974–80. Available from: <http://dx.doi.org/10.1016/j.ijom.2013.03.023>
43. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Schiff base complexes of rare earth metal ions: Synthesis, characterization and catalytic activity for the oxidation of aniline and substituted anilines [Internet]. Vol. 753, *Journal of Organometallic Chemistry*. 2014. p. 72–80. Available from: <http://dx.doi.org/10.1016/j.jorganchem.2013.12.014>
44. Dhinesh B, Isaac Joshua Ramesh Lalvani J, Parthasarathy M, Annamalai K. An assessment on performance, emission and combustion characteristics of single cylinder diesel engine powered by *Cymbopogon flexuosus* biofuel [Internet]. Vol. 117, *Energy Conversion and Management*. 2016. p. 466–74. Available from:

<http://dx.doi.org/10.1016/j.enconman.2016.03.049>

45. PradeepKumar AR, Shemesh H, Jothilatha S, Vijayabharathi R, Jayalakshmi S, Kishen A. Diagnosis of Vertical Root Fractures in Restored Endodontically Treated Teeth: A Time-dependent Retrospective Cohort Study. *J Endod* [Internet]. 2016 Aug;42(8):1175–80. Available from: <http://dx.doi.org/10.1016/j.joen.2016.04.012>
46. Vijayakumar GNS, Nixon Samuel Vijayakumar G, Devashankar S, Rathnakumari M, Sureshkumar P. Synthesis of electrospun ZnO/CuO nanocomposite fibers and their dielectric and non-linear optic studies [Internet]. Vol. 507, *Journal of Alloys and Compounds*. 2010. p. 225–9. Available from: <http://dx.doi.org/10.1016/j.jallcom.2010.07.161>
47. Kavitha M, Subramanian R, Narayanan R, Udhayabanu V. Solution combustion synthesis and characterization of strontium substituted hydroxyapatite nanocrystals [Internet]. Vol. 253, *Powder Technology*. 2014. p. 129–37. Available from: <http://dx.doi.org/10.1016/j.powtec.2013.10.045>
48. Sahu D, Kannan GM, Vijayaraghavan R. Size-Dependent Effect of Zinc Oxide on Toxicity and Inflammatory Potential of Human Monocytes [Internet]. Vol. 77, *Journal of Toxicology and Environmental Health, Part A*. 2014. p. 177–91. Available from: <http://dx.doi.org/10.1080/15287394.2013.853224>
49. Neelakantan P, Cheng CQ, Mohanraj R, Sriraman P, Subbarao C, Sharma S. Antibiofilm activity of three irrigation protocols activated by ultrasonic, diode laser or Er:YAG laser in vitro [Internet]. Vol. 48, *International Endodontic Journal*. 2015. p. 602–10. Available from: <http://dx.doi.org/10.1111/iej.12354>
50. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Synthesis, spectroscopic characterization and antibacterial studies of lanthanide(III) Schiff base complexes containing N, O donor atoms [Internet]. Vols. 1056-1057, *Journal of Molecular Structure*. 2014. p. 307–13. Available from: <http://dx.doi.org/10.1016/j.molstruc.2013.10.014>
51. Gopalakannan S, Senthilvelan T, Ranganathan S. Modeling and Optimization of EDM Process Parameters on Machining of Al 7075-B4C MMC Using RSM [Internet]. Vol. 38, *Procedia Engineering*. 2012. p. 685–90. Available from: <http://dx.doi.org/10.1016/j.proeng.2012.06.086>
52. Parthasarathy M, Isaac JoshuaRamesh Lalvani J, Dhinesh B, Annamalai K. Effect of hydrogen on ethanol-biodiesel blend on performance and emission characteristics of a direct injection diesel engine. *Ecotoxicol Environ Saf* [Internet]. 2016 Dec;134(Pt 2):433–9. Available from: <http://dx.doi.org/10.1016/j.ecoenv.2015.11.005>